



PREFINITO SUPPORTATO (2 strati) engineered flooring (2 layers) pre-finished



essenze woods	selezioni grades		10/4x70x450/500 m/f	10/4x90x600/900 m/f
ACERO EUROPEO EUROPEAN MAPLE	Uni A	Uni A	•	
	Rustica	Rustic	•	
CILIEGIO EUROPEO EUROPEAN CHERRY	Prima	First	•	
	Uni A	Uni A	•	
DOUSSIÈ AFRICA	Prima	First	•	•
	Uni A	Uni A	•	
	Standard	Standard	•	
FAGGIO EVAPORATO STEAMED BEECH	Uni A	Uni A	•	
	Rustica	Rustic	•	
IROKO	Prima	First	•	•
	Uni A	Uni A	•	
	Standard	Standard	•	
ROVERE EUROPEO EUROPEAN OAK	Prima	First	•	•
	Uni A	Uni A	•	•
	Rustica	Rustic	•	
	Natura	Natural	•	
ROVERE EUROPEO Thermo THERMO EUROPEAN OAK	Uni A	Uni A	•	
	Rustica	Rustic	•	
TEAK ASIA TEAK	Prima	First	•	•
	Standard	Standard	•	

Battiscopa "becco di civetta" skirting board

essenze woods	MASSELLO mm. 75x10 SOLID WOOD mm. 75x10	MASSELLO mm. 95x10 SOLID WOOD mm. 95x10	IMPIALLACCIATO mm. 80x10 VENEERING mm. 80x10
ACERO EUROPEO - EUROPEAN MAPLE			•
CILIEGIO EUROPEO - EUROPEAN CHERRY			•
DOUSSIÈ AFRICA	•	•	•
FAGGIO EVAPORATO - STEAMED BEECH			•
IROKO	•	•	•
LACCATO BIANCO - WHITE LACQUERED			•
ROVERE EUROPEO - EUROPEAN OAK	•	•	•
TEAK ASIA - TEAK	•	•	•
WENGÈ - ROVERE THERMO - TH. OAK	•		•

• disponibile/available

PREFINITO SUPPORTATO (2 strati) engineered flooring (2 layers) pre-finished

Metodi di selezione IPF

Prima	Doghe con venatura dritta o leggermente ondulata (rigato largo), possibili arricciature di fibra. È tollerata l'eventuale presenza di piccola macchie caratteristiche della specie, tendenti ad uniformare con l'ossidazione. Selezionata in tre toni: chiaro, medio, scuro. Rovere tonalità unica.
Uni A	Doghe con venatura rigata, fiammata, possibile presenza di piccoli nodi (o.p.). Tollerata la presenza di macchie tipiche della specie, tendenti, talvolta, ad uniformare con l'ossidazione.
Standard	Doghe con venatura prevalentemente ondulata ed irregolare. Presenza di nodi e piccole macchie talvolta tendenti ad uniformare con l'ossidazione. Tonalità non omogenea, presenza di minerale anche marcata (soprattutto nel Doussié Africa) che potrebbe evidenziarsi con la verniciatura. Parzialmente selezionata in due toni.
Rustica	Doghe con nodi, piccole strappature, macchie caratteristiche della specie. Ammessa la presenza di limitati "spicchi" di alborno. Colore non omogeneo. Sono ammesse venature marcate con colorazioni anche contrastanti, tendenti ad uniformare, parzialmente, con l'ossidazione. Frequente presenza di sacche di minerale che si evidenziano con la verniciatura.
Natura	Doghe con venature marcate, fibra anche molto intrecciata, nodi, alborno, sacche di minerale, piccoli difetti di lavorazione e/o incurvature. Non viene selezionata per toni. Disponibile solo nel Rovere.

IPF selection methods

First	Straight or slightly wavy veined listels, small characteristics marks, which tend to diminish with oxidation, are tolerated. Graded in three shades: light, medium and dark. Oak one shade only.
Uni A	Straight strips, flame, possibile presence of small sound knots. Presence of small typical marks, which tend to diminish with oxidation, is tolerated.
Standard	Listels with undulating, oblique and irregular grain. Possible presence of small knots and marks which tend to diminish with oxidation. Differences in colour, mineral traces become evident after varnishing (especially in Doussié Africa). Graded in two shades.
Rustic	Listels with knots, small cracks, typical wood marks. Possible presence of small segments of sapwood. Material partially graded by shade. Differences in colour, which tend to diminish with oxidation, are tolerated. Mineral traces become evident after varnishing.
Natural	Listels with sapwood, cracks mineral traces, small defects due to working and/or curvatures. Not graded according to shade. Available only in Oak.

Specifiche tecniche technical specifications

Formato / Size:	10x70x450/600 m/f 10x90x600/900 m/f
Struttura / Structure:	2 strati (legno nobile mm. 4,00) / 2 layers (top layer mm. 4,00)
Supporto / Bottom layer:	Abete o multistrato fenolico / Pinewood of phonilic plywood Rovere 10x70x490 supporto Rovere o Betulla massello Oak 10x70x490 backing in solid Oak or Birch wood
Trattamento / Treatment:	7 mani UV alta resistenza all'usura 7 coats of UV drying varnish high resistance to wear
Finitura / Finish:	Semilucida 20/25 gloss / semi-gloss 20/25 gloss